


# iQ TORO SC technical data


CLASSIFICATION	STANDARDS	iQ Toro SC
Type of floor covering	ISO 10581	Permanently static dissipative pressed homogeneous vinyl flooring
Classification	EN ISO 10874	Commercial: 34 Industrial: 43
Certification	EN 14041	Yes
CHARACTERISTICS	STANDARDS	iQ Toro SC
Total thickness	EN ISO 24346	2.0 mm
Wear layer thickness	EN ISO 24340	2.0 mm
Total weight	EN ISO 23997	2950 g/m <sup>2</sup>
Binder content	EN ISO 10581 - Compact	Type I
Surface treatment		iQ PUR
Dimensions	EN ISO 24341 Sheet (roll)	Approx. 23 lm x 200 cm Art. no. 3093 ___ 3 digit colour number
	EN ISO 24342 Tile (box)	61x 61 cm - 14 tiles/box = 5.21 m <sup>2</sup> Art. no. 3094 ___ 3 digit colour number
TECHNICAL PERFORMANCES	STANDARDS	iQ Toro SC
Dimensional stability	EN ISO 23999	≤ 0.40% for rolls ≤ 0.25% for tiles
Residual indentation	EN ISO 24343-1	Best measured value: 0.02 mm Required value: ≤ 0.10mm
Effect of castor chair	ISO 4918 - EN 425	Suitable
Clean room test	ASTM F24 F51	Class A
Ease of decontamination	ISO 8690	Good
Light fastness	EN ISO 105-B02	≥ level 7
Total VOC emissions	ISO 16000-6	≤ 10 µg/m <sup>3</sup> (after 28 days)
Bacteria resistance	ISO 846 - Part C	Does not favour growth
Reaction to fire	EN ISO 9239-1 EN ISO 13501-1 EN ISO 11925-2	≥ 8 kW/m <sup>2</sup> Class B <sub>n</sub> s1 Pass
Static electrical charge	EN 1815	< 2 kV
Slip resistance	DIN 51130 EN 13893	≥ 0.3 R9
Seam strength	EN 684	Average value: ≥ 240 N/50 mm Individual values: ≥ 180 N/50 mm
Thermal resistance	EN 12667	Approx. 0.01 m <sup>2</sup> K/W
Electrical insulation	VDE 0100, Part 600	R <sub>i</sub> ≤ 5 x 10 <sup>4</sup> Ohms
Electrical resistance	ESD-approval SP-method 2472 EN 1081	R ≤ 10 <sup>9</sup> Ohms R <sub>1</sub> 5x10 <sup>4</sup> ≤ R ≤ 10 <sup>6</sup> Ohms R <sub>2</sub> 5x10 <sup>4</sup> ≤ R ≤ 10 <sup>6</sup> Ohms R 5x10 <sup>4</sup> ≤ R ≤ 10 <sup>6</sup> Ohms measured to ground
	EN/IEC 61340-4-1 / 100 V EN/IEC 61340-4-5	≤ 3.5x10 <sup>7</sup> Ohms
Chemical resistance	ISO 26987	Excellent
Underfloor heating		Suitable - max. 27°C
Colours		14

The above information is subject to modifications for the benefit of further improvement. (03/17).  
For more detailed technical information, please contact Tarkett.


CUSTOMS TARIFF: 482050000000F



## Logistics Information



## General Information



iQ Toro SC	NCS N°	Welding Rod No.
100	S 1002-Y50R	1287 322
101	S 2502-B	1291 811
102	S 4502-B	1292 383
103	S 8502-B	1292 384
104	S 1005-Y40R	1288 255
105	S 2020-Y30R	1292 372
107	S 2020-R90B	1291 210
570	S 1502-Y50R	1287 531
572	S 1515-Y30R	1287 438
573	S 2030-Y30R	1287 059
574	S 4005-Y50R	1287 379
575	S 7005-Y80R	1287 456
576	S 4020-G50Y	1287 309
578	S 6502-B	1291 216